

Verdcol® Red 170 YO

- Mid shade red
- Good opacity


Colour Index	Pigment Red 170
C.I. No.	12475
CAS No.	2786-76-7
REACH Pre-Registration No.	Available on Request

Physical Data	
Density[g/cm ³]	1.4-1.5
Specific Surface [m ² /g]	15-20
Oil Absorption[g/100g]	60-65
Heat Stability[°C]	160°C

Application	
Automotive Coatings	●
Industrial Coatings	●
Decorative Coatings	●
Powder Coatings	●
Coil Coatings	●
Wood Coatings	●
● : recommended	
○ : limited suitability	
— : not recommended	



Full Shade



Tint 1:25 TiO₂

Fastness						
Light	Weather	Acid	Alkali	BAC	MEK	Xylene
6	4	5	5	4-5	4	4-5

For more details, please contact service@verdcol.com