

Verdcol[®] Violet 23 KR

- Red shade violet
- High gloss

Colour Index	Pigment Violet 23
C.I. No.	51319
CAS No.	6358-30-1
REACH Pre-Registration No.	Available on Request

Physical Data	
Density[g/cm ³]	1.3-1.4
Specific Surface [m ² /g]	55-60
Oil Absorption[g/100g]	75-80
Heat Stability[°C]	200°C

Application	
Automotive Coatings	●
Industrial Coatings	●
Decorative Coatings	●
Powder Coatings	●
Coil Coatings	●
Wood Coatings	●
● : recommended	
○ : limited suitability	
— : not recommended	



Full Shade



Tint 1:25 TiO₂

Fastness						
Light	Weather	Acid	Alkali	BAC	MEK	Xylene
8	4-5	5	5	4	4	4

For more details, please contact service@verdcol.com